

## PRODUCT DESCRIPTION

Premium quality repair filler based on selected polymers developed for the filling of cracks and surface imperfections in concrete and cement based building materials.

## APPLICATIONS

- All surfaces to be leveled should first be wetted with water at least one hour prior to the application of crack filler
- The crack filler is pressed firmly into the crack by using a spatula or putty knife
- Build up the crack filler in thin layers, until any irregularities or protrusions have been completely covered
- For extra smooth surfaces it is recommended to use 2 coats of SAAF Putty 50-8000
- Final coat should be abraded using a fine grain sand paper least 24 hours
- Leveled areas may be over coated with decorative coatings

## ESTIMATING SUPPLY

Crack Filler : 25 kg bags

## COVERAGE AND YIELD

Approximately 40m<sup>2</sup> at 0.5 mm thickness per 25 kg bag

## APPLICATION THICKNESS

0.5 – 4 mm in 2 applications

## APPLICATION ISTRUCTIONS

### SUBSTRATE PREPERATIONS

All surfaces to receive crack filler should be clean and free from dust, coatings, curing compounds and other loose debris. Surfaces to be leveled should first be wetted with water at least one hour prior to the application of crack filler.

## ADDITIONAL INFORMATION

### SAAF IS ALSO MANUFACTURES THE FOLLOWING RANGE OF PRODUCTS

- Solvent Based Adhesives
- Water Based Adhesives
- Flooring Adhesives
- Putties & Sealants
- Coatings
- Concrete Admixtures

For further information, kindly visit our website [www.tigind.com](http://www.tigind.com)

## ADVANTAGES

- Suitable for both Internal and external applications
- Excellent adhesion to host substrate
- Excellent filling, smoothing and leveling properties
- Suitable for over-coating with various paint types
- Can be applied in multiple coats

## MIXING

Mix in a suitable size container using a suitable paddle. Place 7.5 – 9.0 litres of cool, clean water in the mixing container followed by the powder and mix thoroughly. Small quantities can be hand mixed by blending 2.5 - 3 parts powder to 1 part by volume of cool, clean, water.

## STORAGE

- Should be stored away from direct sunlight in a cool, dry, well-ventilated area between 5°C to 39°C
- Protect from freezing

## SHELF LIFE

12 months shelf life when stored in it's original unopened container between 5°C to 39°C.

## HEALTH & SAFETY

Crack Filler contains cement powders, when mixed or become damp, release alkalis which can be harmful to the skin. During use, avoid inhalation of dust and contact with skin and eyes. Wear suitable protective clothing, gloves, eye protection and respiratory protective equipment. The use of barrier creams provides additional skin protection. In case of contact with skin, rinse with plenty of clean water, then cleanse with soap and water. In case of contact with eyes, rinse immediately with plenty of clean water and seek medical advice. If swallowed, seek medical attention immediately - do not induce vomiting.



سأف SAAF

مستانة راسية  
Lasting Foundations

WALL READY CRACK FILLER®

Date: Nov 2016

Version: R 2

Printing date: Nov 2016

# TECHNICAL DATA SHEET

F/QC/13: R2

The information provided here is based on our test results and to the best of our current knowledge. The recommendations and suggestions here in are made to facilitate the application of the product without any guarantee or representation to results. We recommend you to ensure that the product meets all your requirements prior to the application.

SAAF Technologies CO. LTD. • Al Kharj Road kilo -7 • P.O.Box: 8822 Riyadh 11492 • Saudi Arabia • Tel: +966 11 4951844 • Fax: +966 11 4953565 • E-mail: info@saaftech.com